



F10E Intumescent Coating

Technical Data Sheet

ESR-3997

FireShell® F10E is a water-based, single-component, non-flammable, intumescent, interior coating designed to expand in the event of a fire to provide a protective layer of char that could starve fire of oxygen and prevent flame contact with protected surfaces. It is a non-toxic and non-fuming product.

RECOMMENDED SUBSTRATE

- Walls, Attics, Crawl Spaces
- Open cell SPF insulation
- Closed cell SPF insulation
- FRP Panel Systems

APPROVALS

FireShell F10E complies with the 2018 International Building Code requirements for use as an alternative thermal barrier coating system over most SPF insulation systems as per ICC-ES ESR 3997 available at [FireShellCoatings.com](http://www.fireshellcoatings.com) or <http://www.icc-es.org/>.

FireShell F10E carries a multitude of building code, industry, and environmental approvals including:

- Meets IBC 803.1.2.1 for interior surfaces
- Meets IBC 2603.9 over SPF
- Meets IRC R316.6 over SPF
- Meets IRC R302.9.4 for interior surfaces
- E84 Class 'A' rated
- LEED Certified Green Product
- Meets EPA Low-VOC Standard
- FM 4975 Listed Fire-Retardant Paint Over Combustible Surfaces

THICKNESS

Most SPF insulation systems can be coated in a single application to achieve building code compliance. Refer to the F10E product matrix and ICC-ES ESR 3997 available at www.icc-es.org for recommended coverage rates for your specific SPF insulation product.

Should your SPF product require more than one coat to comply with building code, individual coats of FireShell F10E should be applied in perpendicular direction to the previous coat to achieve a cross-hatching application.

The maximum single-pass application rate for FireShell F10E is 27 wet mils.

The actual dry film thickness achieved in the field application is dependent upon many variables including method of application, and surface textures. It is the sole responsibility of the coating

applicator to apply the proper amount of material required to achieve the minimum dry film thickness specified for the given requirements for the project.

To accurately achieve proper coverage applicator must check wet film thickness during application with a wet film gauge on multiple coupons evenly spaced throughout the project application area. Dry film thickness (DFT) is calculated from a measured wet film thickness (WFT) equation as follows:

$$\text{DFT} = \text{WFT} \times \% \text{ solids by volume}$$

To calculate your Theoretical Application Rate (TAR) in gallons per 100 square feet, use the following equation:

$$\text{TAR} = (\text{WFT})/16$$

DO NOT APPLY WHEN SUBSTRATE SURFACE IS BELOW 55 °F, OR WHEN WEATHER CONDITIONS WILL NOT ALLOW ADEQUATE CURING OF THE COATING.

DO NOT APPLY IF RAIN, DEW, OR FREEZING TEMPERATURES ARE LIKELY TO OCCUR BEFORE PRODUCT CAN DRY AND CURE.

DO NOT APPLY WHEN AMBIENT TEMPERATURE IS WITHIN 5 °F OF THE DEW POINT OR IS EXPECTED TO BE WITHIN 5 °F OF THE DEWPOINT WITHIN 24 HOURS FOLLOWING APPLICATION.

STORAGE, MIXING & THINNING

FireShell F10E is available in ready-to-use, factory sealed, standard-sized, five-gallon pails or fifty-five gallon drums. Other container sizes may be available upon request.

DO NOT ALLOW MATERIAL TO FREEZE.

Storage at temperatures below acceptable minimum storage temperature may shorten shelf life. Product warranty is void if material is stored below or above recommended storage temperature.

DO NOT THIN.

PROPERTIES	
Product Specifications	
Viscosity (ASTM D562)	110 – 130 KU
% Solids by Weight	70%
% Solids by Volume (ASTM D2697)	59%
Weight per Gallon (ASTM D1475)	11.5 lbs/gal (+/- 0.3)
pH	6.0 – 7.0
Mold & Fungus Resistance (ASTM D3278)	10; No Mold Growth
Shelf Life	1 year
VOC	< 10 g/L
Colors	White, Charcoal Black, Gray
Packaging	5 gallon pail 55 gallon drum
Storage Temperature	>45°F (>7°C)
Tack Free Time	60 – 90 mins @ 77°F (25°C) & 50% R.H.*
Dry / Recoat Time	2 – 3 hours @ 77°F (25°C) & 50% R.H.*
Sag Resistance	34 mils on walls 24 mils on ceilings*
Processing Pressure	>2200 PSI at the gun tip*
Minimum Material Temperature	>62°F (>17°C)
Ambient Temperature Range	55 – 95°F (13 – 35°C)
Minimum Substrate Temperature	>55°F (>13°C)
Ambient RH% Range	40 – 60% (requires <70%)
Recommended Sprayer	Graco 695 or equivalent (>0.74 gpm delivery rate)
Recommended Gun	Graco HD Texture Gun or equivalent
Recommended Tip Size	.521 – .525 reversible, self-cleaning is recommended
Coverage	80 – 115 sq. ft. per gal**



F10E Intumescent Coating

Technical Data Sheet

STORAGE, MIXING & THINNING CON'T

Prior to use thoroughly mix FireShell F10E with an air or electrically driven power mixer for a minimum of 2-4 minutes or until product color and viscosity is uniform. Mixer speed should be set fast enough to uniformly mix the entire container but not so fast as to introduce air into the coating while mixing. For five-gallon pails use a minimum 3" mixing blade, for drums use a minimum 6" mixing blade.

Previously opened containers, or containers that have been stored for an extended length of time, may develop a skin on top of or at the edges of the coating, which must be removed prior to mixing.

SURFACE PREP

SURFACE TEXTURE OF SPF WILL GREATLY AFFECT MATERIAL ADHESION, SAG RESISTANCE, AND COVERAGE RATE.

SPF surface should have a fine, orange-peel texture (or rougher), and be flat for optimum adhesion and material coverage.

SPF surface that is bumpy, or significantly uneven will decrease coating coverage. SPF that has a glossy or slick appearance may need to be abraded or "scuffed" to roughen the surface to promote adhesion of coating.

SPF surface must be clean, dry and free of any mildew, oil, grease, dirt, or other foreign contaminants that would prevent proper adhesion. Any such contaminants must be removed from the application surface.

For application in high humidity or low temperature environments apply product in thin passes to promote proper drying & curing.

EQUIPMENT

FireShell F10E can be applied with airless spray equipment. Areas requiring special detail or touch up can be brushed or rolled.

When using airless spray equipment ensure the equipment has a volume output not less than 0.74gpm (gallons per minute) and an operating pressure of 3300 psi. The sprayer should be equipped with a filter screen 30-mesh. To ensure proper pressure and delivery to the spray gun use the following rules for hose diameter & length:

- Min. 3/8" ID up to 75'
- Min 1/2" ID up to 200'
- Min 3/4" ID greater than 200'
- Min 3/8" ID & Max 6' L for whip hose

Always use larger diameter hose sections nearest the pump.

We recommend using a Graco Reverse-A-Clean (RAC) X gun tip with no internal diffuser and an orifice size of .521 - .525.

ALWAYS USE EQUIPMENT AND COMPONENTS WITH THE PROPER PRESSURE AND MATERIAL DELIVERY RATINGS THAT ARE IN GOOD WORKING ORDER.

A natural bristle brush or a medium nap roller can be used for touch-up and edge work, or for small areas that are not practical for spray application.

SAFETY & ENVIRONMENTAL

FireShell F10E is installed by independent contractors. It is recommended that building owners verify that your contractor maintains proper credentials, insurance, licenses, and is properly trained to safely install coatings.

FireShell F10E achieves a Class A Fire rating. It is formaldehyde-free, halogen-free, low-VOC, HFC free, and PBDE-free.

Always read and follow all job site safety requirements as set forth by state and federal safety regulatory agencies such as OSHA and NIOSH.

Always read and follow all Material Safety Data Sheets provided with all shipments. Additional copies are available upon request from ICP or your technical representative

Basic PPE safety equipment is required for personal protection including, but not limited to: long-sleeve chemically resistant overalls, rubber gloves, splash shield or safety glasses with splash guards, rubber or leather boots w/ covers.

DO NOT USE NEAR HIGH HEAT OR OPEN FLAME.

DO NOT TAKE INTERNALLY AND PREVENT CONTACT WITH SKIN OR EYES.

KEEP OUT OF THE REACH OF CHILDREN.

CURE TIME & RECOAT

FireShell coatings are latex based. To ensure that successive coats are applied properly, it is important to understand how they dry and cure. As the coating dries, the liquid components evaporate. As liquid evaporates from the coating it becomes cured while the evaporated liquid becomes water vapor suspended in the air surrounding the coating.

The drying time between coats is normally longer than simply "dry to touch" or "tack-free", especially with thicker coating applications. "Dry to touch" or "tack-free" means you can touch a coated surface without getting paint on your hand. While this is a stage in the curing process, this indicates that the liquids have evaporated only from the surface of the paint, and does not mean that the coating is dry enough to add a second coat without creating significantly longer drying time.

Building a thick coating, intentionally or unintentionally, or spraying the coating over an uncured substrate may create problems in the drying and curing process. Until all the liquids have completed evaporated, the coating is not cured. Normal full cure time is 2-4 weeks. Once cured the coating becomes a durable and inert fire protective finish. Even under adverse application conditions, the coating will eventually cure; however, the noncompliant application procedure may affect adhesion quality, lingering odors, drying time, and the warranty of the coating.

ENVIRONMENTAL CONDITIONS & DRYING

Proper ambient air-movement, proper substrate and coating temperatures, and low humidity are necessary for proper adhesion and drying of the coating. The following example illustrates the drying potential of 10,000 ft.3 of air at various temperatures:

- 90°F air can evaporate 2.6 gal of water
- 40°F air can evaporate 0.5 gal of water

FireShell coatings are approximately 68% solids which mean each five-gallon pail of coating contains roughly 1.5 gallons of water that must be evaporated from for the coating to dry and cure.

As a reference, an attic in a 1,600 ft.2 house with a gable roof that has an 8/12 pitch will have an attic volume of approximately 10,600 ft.3. Based on the above illustrations, conditions in this attic would need to be extremely dry with an interior temperature more than 90 °F prior to coating application to be assured of proper drying of one five-gallon pail of coating.

Low temperatures or humidity over 70% RH in the attic prior, during, or after application can hinder drying of the coating and can produce lingering odors due to the slow evaporation of the liquid components.

Odors emitted from the coating as it dries should be similar to those found in low-odor latex paint. Under proper drying conditions these odors should quickly dissipate and not cause any lingering issues.



F10E Intumescent Coating

Technical Data Sheet

ENVIRONMENTAL CONDITIONS & DRYING CON'T

To avoid problems associated with improper drying of the coating always observe Application Procedures and product recommendations.

PRODUCT LIMITATIONS

FireShell F10E should not be used for exterior applications.

It should not be used where it will stay submerged in water or below grade where back-fill material will be in permanent contact with the coating.

FireShell F10E should not be used in areas that are or will be subjected to extreme temperature or humidity conditions such as swimming pool rooms, hot yoga studios, spas, hot tubs, saunas, cold storage, or other areas where temperatures or humidity levels may be abnormally high or low under normal use. Contact your ICP representative if you have questions regarding other extreme use applications.

Installation must comply with all applicable building codes.

VENTILATION

Closed areas, such as unvented attics, will require mechanical, negative-pressure, cross ventilation during the spraying and drying period. Mechanical, negative-pressure, cross ventilation is the ONLY effective method of ventilating closed or confined spaces where coatings must be applied to ensure proper drying.

For ventilation, it is important to ensure you create negative pressure (vacuum) in the enclosed spray area to evacuate water vapor and any off-gassed components of either the SPF insulation system or coating to exterior, unoccupied space. This can be achieved using a whole-house ventilation technique outlined below:

- Review and observe all application parameters, product limitations & recommendations on the technical data sheet to ensure the work environment is suitable for the application of coating.

- Inspect the foam substrate to ensure it is dry, clean and secured to its substrate.
- Use a "supply" blower to draft fresh exterior air to one end of the enclosed space via a hose from the non-occupied exterior.
- Ensure the supply air flows across the immediate vicinity of the spray operation.
- Use an "exhaust" blower to evacuate the stale, moisture laden air from the opposite end of the enclosed space through a hose to the exterior of the building.
- The exhaust blower must have a larger air volume output than the supply blower to ensure the enclosed space is maintained at a negative pressure in relationship to the surround area.
- Do not arrange the ends of the hoses where the supply air is drafting air from the exhaust hose
- Do not exhaust the stale air into any living space or garage area. It must be exhausted to a safe uninhabited open area.
- Place a filter over the exhaust hose to avoid spreading overspray.
- Ensure the lengths of supply and exhaust hoses and filter do not restrict the air movement.
- Constant monitoring of humidity and temperature is necessary until coating has dried thoroughly to ensure the spray environment remains within the application parameters specified on the coating technical data sheet. If the humidity exceeds 70% RH during the drying period while using mechanical, negative-pressure, cross-ventilation, then mechanical dehumidification may be required as supplementary drying aid until the coating is thoroughly dry.

DO NOT USE PROPANE, KEROSENE, OR DIESEL COMBUSTION HEATERS TO HEAT A CLOSED SPACE.

Burning fuels like this in a confined space depletes oxygen and can create a dangerous buildup of toxic gasses including CO and CO₂. Always observe OSHA and NIOSH regulations for using heaters in confined or closed spaces.

In addition, the process of burning fuels such as kerosene, propane, or diesel adds significant amounts of water vapor to the environment, which furthers hinders the evaporative drying process.

DISPOSAL & CLEANUP

Consult Safety Data Sheets (SDS) prior to handling and disposal.

Cured product may be disposed of without restriction. Product containers that are "drip free" may be disposed of according to local, state and federal laws.

Spills or overspray during application can be cleaned/ removed with soap and water for uncured material.

NOTE: Physical properties shown are typical and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions and may vary upon use, temperature, and ambient conditions. Right to change physical properties as a result of technical progress is reserved. Yields shown are optimum and will vary slightly depending on ambient conditions and application. This information supersedes all previously published data. The Customer is responsible for deciding whether products and associated TDS information are appropriate for customer's use.

DISPOSAL: Federal, State and Local regulations. Under the Resource Conservation and Recovery Act (RCRA) regulations, it is the responsibility of the product user to determine, at the time of disposal, whether a material should be classified as a hazardous waste. For recycling guidance of any unused amount, contact your local or provincial organization of recovery and recycling. Dry, empty containers may be recycled in a can recycling program where facilities are available and sanctioned by local authorities.

PRECAUTIONS: Do not mix with other paints, solvents, or colors in oil. Keep from freezing. Air and surface temperature should be above 50°F during application and drying time. Do not paint when rain or dew is imminent.

LIMITED WARRANTY AND LIMITATION OF DAMAGES: ICP Building Solutions Group warrants only that the product shall meet ICP Building Solutions Group's specifications for the product when shipped by ICP Building Solutions Group. NO OTHER EXPRESSED OR IMPLIED WARRANTIES APPLY AND ANY IMPLIED WARRANTIES OF MERCHANTABILITY, NON-INFRINGEMENT OUTSIDE THE U.S. AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. Buyer and users assume all risks of use, handling and storage of the product. Failure to strictly adhere to any recommended procedures shall release ICP Building Solutions Group from all liability. The user of the product is responsible to determine suitability of the product for the particular use. The exclusive remedy as to any breach of warranty, negligence or other claim is limited to the replacement of the product. Liability for any indirect, incidental or consequential damage or loss is specifically excluded.

ENVIRONMENTAL AND SAFETY: Keep out of reach of children. Do not take internally. Close container after use. Refer to Safety Data Sheet for additional health and safety information.